

AKOYA

PC13-003, Aloe

TECHNICAL INFORMATION

CATEGORY: Drapery & Privacy Curtains
 CONTENT: 55% Polyester/45% FR Polyester
 FINISH: None
 WIDTH: 72"
 WEIGHT: 12.24 oz./ln yd
 VISUAL REPEAT: 10.0 in/25.40 cm H, 27.04 in/68.68 cm V
 SHOWN RAILROADED: Yes
 DIRECTIONAL: Yes
 APPROX. ROLL SIZE: 60 yards

PERFORMANCE



ABRASION RESISTANCE: n/a
 BREAKING STRENGTH: Warp 100.0 / Fill 100.0
 COLORFASTNESS TO CROCKING: Dry: Class 4/Wet: Class 3
 COLORFASTNESS TO LIGHT: 60 hours
 PILLING RESISTANCE: Class n/a
 SEAM SLIPPAGE: Warp 97.0 / Fill 66.0

FLAMMABILITY

PASSES CAL TB 117-2013
 NFPA 260/UFAC CLASS 1
 NFPA 701 (TEST#1)



REDUCED ENVIRONMENTAL IMPACT

GREENGUARD GOLD CERTIFIED
 PFAS FREE
 MINDFUL MATERIALS COMPLIANT
 PROP 65 COMPLIANT
 REACH COMPLIANT
 ROHS COMPLIANT
 DOES NOT CONTAIN CONFLICT MINERALS
 BERRY COMPLIANT
 MILLED IN AMERICA

WARRANTY

PRIVACY CURTAIN | '3' THREE YEAR WARRANTY
See [Warranty Terms](#) for more information.

ADDITIONAL INFORMATION

Custom Colors: All patterns can be custom colored. Minimum yardage applies.

Digital Swatch Color Matching: Due to color variations on different monitors and color printers, actual swatch colors may vary slightly. Please request a memo sample from Mayer Fabrics to ensure proper color representation.

CLEANING & MAINTENANCE

PC: Privacy Curtains Cleaning Info - Wash Cycle: Process Cubicle fabric as any ordinary colored fabric, temperature not to exceed 160F. Use a synthetic detergent. Add softener to the last rinse cycle. Extracting Cycle: Fabric requires no more than 2-4 min. extracting, depending on size of load and equipment used. Drying Cycle: Do not overload dryer. Tumble dry for 3-5 min. on synthetic cycle 110F. As with all polyester fabrics, excessive heat will detract from the permanent press characteristics of this fabric. Finishing: If fabric is folded upon completion of the drying cycle, no finishing is required. Occasional light touch-up with a hand iron (275F max), or using a flat bed press with covered head may be desired for smoother seams. Important: Use cover cloth between fabric and iron or pressing head. Avoid prolonged contact with heat. Notes: Do not use caustic soap or bleach. Do not put through a mangle.