

**EDEN**

PC15-014, Oasis

**TECHNICAL INFORMATION**

CATEGORY: Drapery & Privacy Curtains  
CONTENT: 35% FR Polyester/35% Recycled Polyester (18% Pre-/17% Post-Consumer)/30% Polyester  
FINISH: None  
WIDTH: 72"  
WEIGHT: 17.66 oz./ln yd  
VISUAL REPEAT: 17.188 in/43.66 cm H, 18.25 in/46.36 cm V  
SHOWN RAILROADED: Yes  
DIRECTIONAL: Yes  
APPROX. ROLL SIZE: 65 yards

**PERFORMANCE**



BREAKING STRENGTH: Warp 212.0 / Fill 353.0  
COLORFASTNESS TO CROCKING: Dry: Class 4 min/Wet: Class 3 min  
COLORFASTNESS TO LIGHT: 4 min at 60 hours  
PILLING RESISTANCE: Class n/a  
SEAM SLIPPAGE: Warp 83.0 / Fill 106.0

**FLAMMABILITY**

PASSES CAL TB 117-2013  
NFPA 260/UFAC CLASS 1  
NFPA 701 (TEST#1)



**REDUCED ENVIRONMENTAL IMPACT**

GREENGUARD GOLD CERTIFIED  
PFAS FREE  
HHI / GREENHEALTH COMPLIANT  
NO ANTIMICROBIAL ADDITIVES  
FORMALDEHYDE FREE  
PROP 65 COMPLIANT  
MILLED IN AMERICA  
DOES NOT CONTAIN CONFLICT MINERALS

## WARRANTY

PRIVACY CURTAIN | '3' THREE YEAR WARRANTY  
See [Warranty Terms](#) for more information.

## ADDITIONAL INFORMATION

Custom Colors: All patterns can be custom colored. Minimum yardage applies.

Digital Swatch Color Matching: Due to color variations on different monitors and color printers, actual swatch colors may vary slightly. Please request a memo sample from Mayer Fabrics to ensure proper color representation.



% of sales from this pattern will be donated to The Common Thread for the Cure.

## CLEANING & MAINTENANCE

PC: Privacy Curtains Cleaning Info - Wash Cycle: Process Cubicle fabric as any ordinary colored fabric, temperature not to exceed 160F. Use a synthetic detergent. Add softener to the last rinse cycle. Extracting Cycle: Fabric requires no more than 2-4 min. extracting, depending on size of load and equipment used. Drying Cycle: Do not overload dryer. Tumble dry for 3-5 min. on synthetic cycle 110F. As with all polyester fabrics, excessive heat will detract from the permanent press characteristics of this fabric. Finishing: If fabric is folded upon completion of the drying cycle, no finishing is required. Occasional light touch-up with a hand iron (275F max), or using a flat bed press with covered head may be desired for smoother seams. Important: Use cover cloth between fabric and iron or pressing head. Avoid prolonged contact with heat. Notes: Do not use caustic soap or bleach. Do not put through a mangler.